

DATA SHEET 22VK0.100.44000

Signolit SIVK

Clear vinyl calandered, monomeric removable acrylic adhesive film. Ideal for stickers, signs, decals and mock-ups. It sticks to most clean surfaces.

Printing Systems



Formats

Art.Number	Thickness	Format	Packing quantity
22VK0.100.44000	0.110 mm	DIN A4	100 sheets
22VK0.100.44700	0.110 mm	DIN A4	250 sheets
22VK0.100.43100	0.110 mm	DIN A3	40 sheets

Technical data

Characteristic



- High brilliance of colours
- Adhesive light
- Universal use

Finish

- Clear glossy
- self-adhesive with paper backing

Specifications

Release liner	siliconized paper ~ 0.145 mm
Coating Printsides	Power-Gloss®, clear glossy

Width (mm)	210
Thickness base material with inkjet coating	0.110 mm
Format	DIN A4
Adhesion strength	~ 7.5 N / 25 mm (A.F.E.R.A.), after 24 h ~ 10 N / 25 mm (A.F.E.R.A.)
Type of adhesive	polyacrylate dispersion, semipermanent
Length (mm)	297
Base Material	calendered monomeric plasticized PVC, 0.100 mm
Total thickness	0.260 mm
Packing quantity	100 sheets

Compatibility

- For use on most Small Format Ink Jet Printers such as: HP, Canon, Epson, Apple, Digital, Kodak, Lexmark, Olivetti, Tektronix, Xerox, etc.

Handling

- Laminating: The printed surface must be protected with foils for cold lamination if it is subject to humidity, sweaty hands, abrasion or any other influences. For a short term outdoor use, SIVK must always be protected with a 5mm overlapping lamination.
- Gluing: SIVK will stick to any solid, smooth surfaces which are dry and free of dirt, grease, silicon etc. Before gluing it is absolutely necessary to check that the surface is appropriate to this aim and that it has been prepared (cleaned) professionally. During gluing the temperature must reach at least 15°C. You can remove SIVK by heating the film's surface with a hot air gun. Then pull it off carefully.

Storage

- Store in a cool and dry place

Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. These shall be beyond our control, and be subject to your exclusive responsibility. The sale of our products shall be subject to our current General Terms and Conditions.